

Serial No. 09/785,436

*El
concl'd* bonding may preferably be carried out under conditions of a temperature of from 100°C to 250°C, a press time of from 0.1 second to 20 seconds and a pressure of from 4 gf/mm² to 200 gf/mm².
